



1134 Manor St. • Bakersfield, CA 93308 / P.O. Box 5877 • Bakersfield, CA 93388  
 Phone 661.393.7110 – www.tricorrefining.com

## CYCLOGEN® LE Specification

<b>Tests (All Tests ASTM Unless Otherwise Stated)</b>		<b>Typical Test</b>	<b>Specification</b>	
			<b>Min.</b>	<b>Max.</b>
VISCOSITY, 25C, SSF	D-244	35.8	15.0	40.0
SIEVE, W%	D-244	0.01		0.10
RESIDUE, W%	D-244	62.2	60.0	
VISCOSITY, 60 C, CST		450	200	500
PARTICLE CHARGE TEST	D-244	POS	POS	
PH OF EMULSION	D-244	5.4		
CEMENT MIXING TEST	D-244	NIL		2.00