



TRICOR REFINING, LLC

Producers of GOLDEN BEAR PRESERVATION PRODUCTS

1134 Manor St. • Oildale, CA 93308 / P.O. Box 5877 • Bakersfield, CA 93388
Phone 661.393.7110 – Fax 661.393.2083

SPECIFICATIONS FOR MC-70

| Test Description | Requirements | |
|--|--------------|------------|
| | MIN | MAX |
| Kinematic Viscosity at 140F (AASHTO T201) | 70 | 140 |
| Flash Point (AASHTO T79) | 100F | |
| Water Percent | | 0.2 |
| Distillation Test (AASHTO T78): | | |
| Asphaltic Residue from Distillation | 55% | |
| Volume Percentage of Total Distillates: | | |
| to 225° C (437° F) | 0 | 20 |
| to 260° C (500° F) | 20 | 60 |
| to 315° C (600° F) | 65 | 90 |
| Tests on Residue from Distillation: | | |
| Absolute Viscosity at 140F (AASHTO T202) | 300 poise | 1200 poise |
| Ductility 5cm/min. (AASHTO T51) | | |
| at 77F | 100cm | |
| at 60F | 100cm | |
| Solubility in Trichloroethylene (AASHTO T44) | 99.0% | |